

**PCT**

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup> :</b>  G03C 1/005	<b>A1</b>	<b>(11) International Publication Number:</b> WO 93/18434  <b>(43) International Publication Date:</b> 16 September 1993 (16.09.93)
<b>(21) International Application Number:</b> PCT/US92/01690 <b>(22) International Filing Date:</b> 12 March 1992 (12.03.92)  <b>(71) Applicant:</b> E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).  <b>(72) Inventor:</b> LeSTRANGE, Raymond, Joseph ; 1720 Hummingbird Lane, Hendersonville, NC 28792 (US).  <b>(74) Agents:</b> GOLIAN, Andrew, G. et al.; E.I. du Pont de Nemours and Company, Legal/Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).  <b>(81) Designated States:</b> AU, CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IT, LU, MC, NL, SE).		<b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> PHOTOGRAPHIC FILM WITH IMPROVED SPEED TO FOG RATIO  <b>(57) Abstract</b>  Photographic, gelatino, silver halide emulsions exhibiting improved speed/fog ratio and good hardening are described. These emulsions are made by sensitizing with 1-naphthol-4-sulfonic acid and by adding an aliphatic polyol thereto.		

**BEST AVAILABLE COPY**

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LJ	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TC	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

TITLE

## PHOTOGRAPHIC FILM WITH IMPROVED SPEED TO FOG RATIO

5 Field of the Invention:

This invention relates to the sensitization of gelatino, silver halide emulsions and to a method for improving the speed/fog ratio of said emulsions. Still more particularly, this invention relates to the  
10 addition of an aliphatic polyol to improve said speed/fog ratio.

Background of the Invention:

In my previously issued U.S. Patent 4,965,184 the use of 1-naphthol-4-sulfonic acid to improve the  
15 sensitization of a gelatino, silver halide emulsion is described. This compound is unusual in and of itself for use as such a sensitizer. Prior art sulfonic acids did not accomplish this increase in speed. The use of a chemical sensitizer usually results in a concurrent  
20 increase in emulsion fog and thus it is conventional to add an antifoggant or stabilizer to control this fog. The use of the latter compounds, although efficacious, usually results in a long term speed loss for the film element. Thus, there have been a continuing effort to  
25 find compounds or combinations of compounds which not only result in a higher level of sensitization but which will reduce the amount of fog generated.

SUMMARY OF THE INVENTION

It is an object of this invention to sensitize  
30 gelatino, silver halide emulsions without generating excess fog. These and yet other objects are achieved by formation of a photosensitive element having at least one photosensitive silver halide emulsion layer containing a sensitizing amount of an alkali metal salt

of 1-naphthol-4-sulfonic acid in a concentration of from 1 to 20 grams per 1.5 moles of silver halide present, wherein the improvement comprises said emulsion containing an aliphatic polyol wherein the speed to fog  
5 ratio of said element is improved.

#### DETAILS OF THE INVENTION

The use of 1-naphthol-4-sulfonic acid and the alkali metal salts thereof is fully described in the  
10 aforementioned application, the substance of which is incorporated herein by reference. This material can be added to gelatino, silver halide emulsion in amounts ranging from 1 to 20 gm/1.5 mole of silver halide present, with 2 to 8 gm/1.5 mole of silver halide being  
15 preferred. The addition of this sensitizer will result in an increase of emulsion speed. However, some increase in emulsion fog has also been noted.

The emulsions useful within the ambit of this invention include all of the common silver halides  
20 including silver bromide, silver iodide and silver chloride or mixtures of two or more of these halides. A particularly preferred emulsion is one of ca. 98 mol % bromide and ca. 2 mol % iodide with fairly large grains. These grains can be any of the commonly known grains  
25 such as cubic, rhombic, tetrahedral and tabular shapes, for example. They can be used in any of the well-known systems such as in graphic arts, cine, X-ray, etc. They may be either positive or negative working systems and the method for producing such elements is well-known to  
30 those of normal skill in the art.

These emulsions can also contain other sensitizers in addition to the 1-naphthol-4-sulfonic acid. The chemical sensitizers with labile sulfur are well-known, for example, and include thiosulfates, thiocyanates,

thionex, etc. Metal salts such as gold and mercury salts may also be present if required. The usual antifoggants, stabilizers, antistatic agents, hardeners, coating and wetting aids, etc., may also be present as well as dyes to improve the sensitivity of the emulsion to different wave lengths.

The organic polyols of this invention are aliphatic and particularly aliphatic polyols containing from 3 to 10 carbon atoms. Examples include 1,2,6-trihydroxyhexane; trimethylolpropane; 1,4-butanediol; 1,5-pentanediol; 1,2-hexanediol; 1,6-hexanediol; and 1,9-nonanediol. These polyols can be added to the emulsion in amounts ranging from 0.5 to 20 gm/1.5 moles of silver halide and preferably in amounts ranging from 2 to 10 gm/1.5 moles of silver halide. They can be added at any time during the emulsion making process but I prefer adding them directly after the aforementioned chemical sensitization step and just prior to the coating of the emulsion on a suitable support. The addition of these aliphatic polyols also help to increase the hardening of the emulsion and lessen the need for additional conventional hardener. This fact helps in emulsion drying during the coating thereof and increases the melting point of the processed films made thereby.

Suitable supports include any of the prior art supports useful for photographic emulsions. Preferably, the support will be a dimensionally stable polyethylene terephthalate support on which will be coated a thin, organic, anchoring substratum followed by another substrate of gelatin. The support may contain other ingredients such as dyes or reflecting agents and alternate layers such as antistatic layers, antihalation

layers, antiabrasion layers may also be present within the metes and bounds of this invention.

This invention will now be demonstrated by the following specific examples of which Example 1 is  
5 considered to be the best mode. All parts and percentages are by weight unless otherwise indicated.

#### EXAMPLE 1

A coarse grained, gelatino, silver halide emulsion  
10 of ca. 98 mol % bromide and ca. 2 mol % iodide was prepared. This emulsion was brought to its optimum sensitivity with gold and sulfur as is well-known to those skilled in the art. Then, it was split into eight  
(8) portions to which the following ingredients were  
15 added as shown in the Table below. Each portion also received a normal aliquot of antifoggants, stabilizers, hardeners, coating and wetting aides before being coated on a 7 mil, blue tinted, polyethylene terephthalate film support previously described above. Each coating was  
20 dried and sampled and each sample given a P45 phosphor screen exposure which is conventional for video imaging applications. The exposed films were developed, fixed, washed and dried in a conventional manner and the sensitometric results are shown in the Table below:

25

TABLE 1

	Compounds Added (gm/1.5 moles of Ag halide)		Sensitometry			Melt
	1-N-4-S	HXT	Speed	Gradient	B+F	
5	0	0	214	5.13	.21	69
	2	0	227	5.34	.19	65
	4	0	227	5.41	.17	63
	0	7.5	210	5.11	.18	70
	0	15.0	207	5.11	.16	72
10	2	7.5	222	5.29	.17	69
	4	10.0	220	5.25	.15	69

1-N-4-S is 1-Naphthol-4-Sulfonic Acid, Sodium Salt

HXT is 1,2,6-trihydroxyhexane

15

As can easily be seen, the combination of ingredients gives the best emulsion sensitometry and the best speed/fog ratio.

20

EXAMPLE 2

In this example, the same emulsion described in Example 1 was used. This emulsion was split into nine (9) portions to which various aliphatic polyols were added. In addition, 4 gm/1.5 mole of silver halide of the sodium salt of 1-naphthol-4-sulfonic acid were also added. One (1) portion was kept as control (neither 1-N-4-S or an aliphatic diol added and one (1) portion had only the 1-N-4-S alone). Each sample was coated, overcoated, dried, exposed, developed, fixed, washed, dried and sampled as described in Example 1. The sensitometric results are shown in the following Table:

TABLE 2

Sensitometry						
	Compounds Added	Amt	Speed	Gradient	B+F	Melt. Pt.
	None - Control		230	3.24	.20	60
5	Only 1-N-4-S		235	3.30	.19	55
	1,2,6-Trihydroxy-					
	hexane	5	223	3.09	.17	64
	Trimethylpropane	5	271	3.30	.18	61
	1,4-Butanediol	10	239	3.08	.18	58
10	1,5-Pentanediol	10	248	3.11	.17	56
	1,2-Hexanediol	10	231	3.02	.17	60
	1,6-Hexanediol	10	228	3.35	.17	55
	1,9-Nonanediol	10	262	3.32	.19	60

## WHAT IS CLAIMED IS:

1. In a photosensitive element having at least one photosensitive silver halide emulsion layer containing a sensitizing amount of an alkali metal salt of 1-naphthol-4-sulfonic acid in a concentration of from  
5 1 to 20 grams per 1.5 moles of silver halide present, wherein the improvement comprises said emulsion containing an aliphatic polyol wherein the speed to fog ratio of said element is improved.
- 10 2. The photosensitive element of claim 1 wherein the polyol contains from 3 to 10 carbon atoms.
3. The element of Claim 2 wherein said aliphatic polyol is taken from the group consisting of 1,2,6-trihydroxyhexane; trimethylpropane; 1,4-butanediol;  
15 1,5-pentanediol; 1,2-hexanediol; 1,6-hexanediol; and 1,9-nonanediol.
4. The element of Claim 2 wherein said aliphatic polyol is present in a range of from 0.5 to 20 gm/1.5 mole of silver halide present.

# INTERNATIONAL SEARCH REPORT

International Application No PCT/US 92/01690

<b>I. CLASSIFICATION OF SUBJECT MATTER</b> (If several classification symbols apply, indicate all) <sup>6</sup> According to International Patent Classification (IPC) or to both National Classification and IPC <b>IPC5: G 03 C 1/005</b>		
<b>II. FIELDS SEARCHED</b>		
Minimum Documentation Searched <sup>7</sup>		
Classification System	Classification Symbols	
IPC5	G 03 C	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in Fields Searched <sup>8</sup>		
<b>III. DOCUMENTS CONSIDERED TO BE RELEVANT<sup>9</sup></b>		
Category *	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>
Y	US, A, 4965184 (LESTRANGE) 23 October 1990, see claim 1  --	1-4
Y	US, A, 3898089 (YAMAMOTO ET AL) 5 August 1975, see claims 1,8  --  -----	1-4
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p><b>* Special categories of cited documents:</b> <sup>10</sup></p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance, the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance, the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&amp;" document member of the same patent family</p> </div> </div>		
<b>IV. CERTIFICATION</b>		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
4th November 1992	13 NOV 1992	
International Searching Authority	Signature of Authorized Officer	
EUROPEAN PATENT OFFICE	Anita Skeppstedt	

**ANNEX TO THE INTERNATIONAL SEARCH REPORT  
ON INTERNATIONAL PATENT APPLICATION NO. PCT/US 92/01690**

**SA 61747**

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.  
The members are as contained in the European Patent Office EDP file on 30/09/92  
The European Patent office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A- 4965184	23/10/90	CA-A- 2010620 EP-A- 0384444	23/08/90 29/08/90
US-A- 3898089	05/08/75	BE-A- 807852 DE-A- 2359345 FR-A-B- 2208134 GB-A- 1394659 JP-C- 900794 JP-A- 49081024 JP-B- 52031737	15/03/74 12/06/74 21/06/74 21/05/75 15/03/78 05/08/74 17/08/77

For more details about this annex : see Official Journal of the European patent Office, No. 12/82

**THIS PAGE BLANK (USPTO)**

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER: \_\_\_\_\_**

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**

**THIS PAGE BLANK (USFTO)**